

MAX-A-SEAL ASPHALT PAINT

Quick Drying Asphalt Paint



DESCRIPTION

MAX-A-SEAL ASPHALT PAINT is a quick drying, high gloss, bituminous, corrosion resistant asphalt paint and offers one coat coverage with full resistance to water, acids, alkalis, electrolysis, and natural elements.

MAX-A-SEAL ASPHALT PAINT is NSF/ANSI 61, approved for use with Potable Water Systems. Federal Specification TTC-494 Types I, II, and III, and AASHTO M 190.

RECOMMENDED USES

Painting metal, masonry, concrete pipe* and wood surfaces, inside and out where a corrosion resistance black protective coating is desired. Excellent for stormwater immersion and is approved for use in stormwater wet wells, pump stations, manholes, and excellent for acid/corrosion protection. Withstands a pH range of 3-10.

Excellent for use on:

- Above/Below Ground Pipelines and valves
- Expose steel in corrosive environments
- Metal Natural Gas Piping
- Storage Tanks/Grease Traps
- Concrete and Concrete Pipe
- Iron Manhole Covers
- Steel to be imbedded in Concrete
- Burial Vaults

APPLICATION

MAX-A-SEAL ASPHALT PAINT must be applied to a clean dry surface free of foreign matter. **MAX-A-SEAL ASPHALT PAINT** will dry within an hour and can be re-coated or backfilled within 5 hours @ 70F. Material should remain dry until it has cured.

This material can be applied by brush, heavy nap roller, or spray equipment at the recommended minimum wet mil thickness of 5 mils at 250-300 ft²/gal.

Max-A-Seal Asphalt Paint is easily sprayed with a Graco GH833 Siphon Pump, 1/2" hose, Blue Texture Spray gun, and a GHD 661 Spray Tip. The Graco GH733 Siphon Pump can also be used with a compatible spray tip. **In both cases, the in-line filter should be removed.**

Other comparable brand spraying equipment can also be used.

Product can be applied surface and air temperatures are at 35° F and rising and can also be applied to "green" concrete.



Clean-Up

Use soap and water for personal clean up, preferable before the material dries. Use **SpecChem Orange Peel** to clean tools and equipment and as a general asphalt cleaner/remover for all **Max-A-Guard Products**.

SPECIFICATIONS/COMPLIANCES

Federal Specification TTC-494 Types I,II, and III, AASHTO-M-190

NSF/ANSI 61 approved for use with Potable Water Systems.

Complies with current federal, state, and local maximum allowable VOC requirements.

PACKAGING

- 1 gallon cans (3.8L)
- 5 gallon pails (18.9 L)
- 55 gallon drums (208.2 L)

SHELF LIFE / STORAGE

Shelf life of **MAX-A-SEAL ASPHALT PAINT** in the original, tightly closed container is 1 year from the date of manufacture. Do not store at temps exceeding 110° F.

TECHNICAL DATA SPECIFICATIONS

Appearance	Glossy Black
Solids (%) (ASTM C1250)	>70% by weight
Density	7.5 lbs/gal
Viscosity SFS @ 122°F	135 cps
Application	Airless Spray, Brush
Cure/Backfill Time	5 hours
Dry Time	1 hour
Application Range	35°F and above
Flash Point ASTM D 92	110°F

TECHNICAL SERVICES

For assistance, contact technical services at:
866-791-8700 816-968-5600
www.specchemllc.com



1511 Baltimore Ave, Suite 600
Kansas City, MO 64108
www.specchemllc.com 866.791.8700

LIMITATIONS / PRECAUTIONS

- Keep material warm before use in cold weather
- Do not allow material to freeze.
- Do not thin material
- Keep out of the reach of children.
- Do not take internally.
- In case of ingestion, CALL A PHYSICIAN immediately. DO NOT induce vomiting.
- Can cause skin irritation upon contact, especially prolonged or repeated. If skin contact occurs, wash immediately with soap and water and seek medical help as needed.
- If eye contact occurs, flush immediately with clean water and seek medical help as needed.
- Refer to Safety Data Sheet for complete health and safety information prior to using product.

WARRANTY

NOTICE-READ CAREFULLY CONDITIONS OF SALE

SpecChem offers this product for sale subject to and limited by the warranty which may only be varied by written agreement of a duly authorized corporate officer of SpecChem. No other representative of or for SpecChem is authorized to grant any warranty or to waive limitation of liability set forth below.

WARRANTY LIMITATION

SpecChem warrants this product to be free of manufacturing defects. If the product when purchased was defective and was within use period indicated on container or carton, when used, SpecChem will replace the defective product with new product without charge to the purchaser. SpecChem makes no other warranty, either expressed or implied, concerning this product. There is no warranty of merchantability. NO CLAIM OF ANY KIND SHALL BE GREATER THAN THE PURCHASE PRICE OF THE PRODUCT IN RESPECT OF WHICH DAMAGES ARE CLAIMED.

INHERENT RISK

Purchaser assumes all risk associated with the use or application of the product.



1511 Baltimore Ave, Suite 600
Kansas City, MO 64108
www.specchemllc.com 866.791.8700