

MVM PRIME 5000

Alkali-Resistant, Epoxy Moisture Control Barrier/Primer



DESCRIPTION

MVM PRIME 5000 is a 2-component, 100% solids epoxy moisture barrier system designed to effectively stop moisture vapor related problems on concrete prior to installing SpecChem underlayments or overlayments. MVM PRIME 5000 also provides an excellent bond to concrete and can be applied to concrete as early as 5 days old where early application of floor covering is required.

Applications for MVM PRIME 5000:

- Prevents moisture related problems with floor covering over concrete floors
- Excellent primer for SpecChem Underlayments/Overlayments

FEATURES/BENEFITS

- One-Coat epoxy system
- Easy to spread/excellent coverage
- VOC Compliant, VOC = 0 grams/liter
- Reduces moisture vapor for floor coverings
- ASTM E 96 = .06 perms @ 14 mils
- Excellent bond strength to concrete

APPEARANCE

MVM PRIME 5000 is a 2-component epoxy system consisting of 2 Parts A (resin) & 1 Part B (hardener).

COVERAGE

Coverage rate is approximately 75-125 sq-ft per gallon. The concrete surface texture greatly affects coverage rates and final appearance.

Material Requirements: A one coat application using a coverage rate of 110 sq-ft per gallon per coat, will create a 14.5 mil coating.

APPLICATION

Concrete Surface Preparation: New Concrete must be a minimum of 5 days old with all curing compounds and sealers removed. Concrete must have a minimum tensile strength of 150 psi.

The existing concrete must be clean, dry and sound. All oil, dirt, debris, paint and unsound concrete must be removed.

The concrete surface must be prepared mechanically using shotblast to a minimum ICRI concrete surface profile of 3 (CSP #3). Acid etching is not acceptable.

Joints and Cracks: All dormant cracks and joints and should be filled using a 100% solids low viscosity epoxy resin such as SpecPoxy 500 or 1000 and sand applied to rejection to the surface while the epoxy is still wet. Excess sand must be removed before the MVM Prime 5000 is applied.

SpecChem cannot be responsible for issues regarding expansion, isolation or moving joints or cracks that may develop, shrink or expand after installation of MVM PRIME 5000.

Recommended Tools: Epoxy mixing paddle, low speed drill, short-nap paint roller or notched squeegee or long-nap paint roller, depending on smooth or uneven surfaces) and paint-brush.

Mixing: All materials should be conditioned in the proper temperature range of 65°F to 85°F. Mix parts A and part B separately for one minute using a drill and mixing prop. For ease of mixing, add 1- Part B to 2- Parts A (not the reverse).

Mix the Part A and Part B together for 3 minutes. Once mixed, pour some of the epoxy back into the hardener container, mix for 30 seconds, then pour all of the contents back into the resin container, ensuring that no hardener residue remains unreacted. The epoxy must be well mixed to ensure proper chemical reaction. **After mixing, place immediately on the prepared surface.**

Placement: This product should be spread with a squeegee or notched squeegee and back rolled with a roller. After application, it is suggested the coating be back-rolled with a spiked roller to reduce surface imperfections, entrapped air and to improve bond.

Sand Broadcast: While MVM PRIME 5000 is still freshly applied (<20 minutes) broadcast clean/dry sand (minus #30 or #16/40) to rejection, consistently over entire application area. Use approximately 1lb sand per square feet of area.

Once broadcast is complete, avoid surface traffic for a minimum of 4 hours. Broom sweep and vacuum surface after 4 hours or whenever the sand is completely adhered, removing all loose sand, leaving an ideal bonding surface for SpecChem underlayment or overlayment systems.

Installing Directly to Flooring: Non-adhering and direct-bond flooring systems may be installed directly to unsanded MVM PRIME 5000 without use of an underlayment product. MVM PRIME 5000 must cure at least 4 hours. Installation of floor covering must not compromise MVM PRIME 5000 application in any way, and only adhesives suitable for use over non-porous substrates may be used.

Care should be taken to ensure that no absorption of any liq-



1511 Baltimore Ave, Suite 600
Kansas City, MO 64108

www.specchemllc.com

866.791.8700

uids, including water, solvents, or otherwise, into the MVM PRIME 5000 takes place. Extended curing time may be required, per manufacturer's recommendations, when installing pressure sensitive adhesives directly to MVM PRIME 5000. Additionally, for adhesives specified for use over a porous substrate, a cementitious underlayment with a minimum thickness of 1/8" must be installed over MVM PRIME 5000.

	Sand Broadcast Required:	Minimum Installation Thickness:	Approx. Application Rate/Gallon
Underlayments Greater than 1/4" (6mm)	<i>Yes</i>	<i>14 mils</i>	<i>100-110 sq. ft.</i>
Toppings	<i>Yes</i>	<i>14 mils</i>	<i>100-110 sq. ft.</i>
Direct Installation of Floor Coverings (No Underlayment)	<i>No</i>	<i>10 mils</i>	<i>150-160 sq. ft.</i>

TYPICAL TEST DATA

The following results were developed under laboratory conditions based on 70°F application. The properties below are typical values, and should not be considered specifications.

Mix Ratio:	2-to-1 Mix Ratio
Permeability (ASTM E 96):	0.06 perms @ 14 mils
Viscosity:	approx. 250 cps
Working Time:	20 Minutes
Walkable:	4 Hours @ 75F
Install Underlayment of topping:	Min. 4 hours
Packaging:	3.0 g/l unit; 15 g/l units

CLEAN UP

Clean tools and equipment before the epoxy has hardened with solvent such as SpecChem SOLVENT 100, Orange Peel or Berry Clean. Do not allow to harden on equipment or mechanical removal will be required.

PACKAGING

3 gallon units (2 -1 gal. Part A Resin & 1-gal. Part B Hardener)
15 gallon units (2 - 5 gal pails Part A, 1- 5 gal Part B)

SHELF LIFE/STORAGE

The shelf life of properly stored MVM PRIME 5000 is two years from date of manufacture. Store MVM PRIME 5000 in its original containers and keep tightly closed in a cool, dry area. Do not allow the accumulation of water, dirt or other contaminants. Do not leave containers exposed to sun. Keep from freezing. Keep away from heat.

SPECIFICATIONS/COMPLIANCES

MVM PRIME 5000 is USDA accepted .

LIMITATIONS/PRECAUTIONS

- Store and condition the product indoors at 50°F to 80°F prior to application. Avoid application at air and floor temperatures below 50°F and high humidity conditions.
- Suitable for service temperature from 40F to 90F.
- Do not install over wood underlayments, gypsum-based underlayments, or concrete slabs subject to freeze-thaw cycles.
- Not suitable as a final wear surface. Flooring surface/system must be installed and all expansion/control/moving joints must be honored and maintained.
- Epoxy components may cause irritation. Avoid contact with eyes and skin.
- Do not apply over hardened primer or old epoxy without proper surface preparation.
- Use in a well ventilated area, keep away from sparks and open flames.
- If HVAC intake ducts will distribute epoxy odor into adjoining occupied areas of the building , care should be taken to block these ventilation vents.

WARRANTY

NOTICE-READ CAREFULLY CONDITIONS OF SALE

SpecChem offers this product for sale subject to and limited by the warranty which may only be varied by written agreement of a duly authorized corporate officer of SpecChem. No other representative of or for SpecChem is authorized to grant any warranty or to waive limitation of liability set forth below.

WARRANTY LIMITATION

SpecChem warrants this product to be free of manufacturing defects. If the product when purchased was defective and was within use period indicated on container or carton, when used, SpecChem will replace the defective product with new product without charge to the purchaser. SpecChem makes no other warranty, either expressed or implied, concerning this product. There is no warranty of merchantability. NO CLAIM OF ANY KIND SHALL BE GREATER THAN THE PURCHASE PRICE OF THE PRODUCT IN RESPECT OF WHICH DAMAGES ARE CLAIMED.

INHERENT RISK

Purchaser assumes all risk associated with the use or application of the product.



1511 Baltimore Ave, Suite 600
Kansas City, MO 64108

www.specchemllc.com

866.791.8700