

Final Finish™



Rapid-hardening/Polymer-modified/Concrete Resurfacer

DESCRIPTION

FINAL FINISH™ is a sand-less, one-component, rapid-hardening, polymer-modified, concrete resurfacing mortar for smoothing, resurfacing, rubbing, and restoring concrete surfaces. FINAL FINISH™ offers a unique long pot life but rapid-hardening performance on the substrate to minimize waste and labor.

FINAL FINISH contain no crystalline silica for ultra-fine repairs.

FINAL FINISH™ offers superior durability for all interior and exterior, horizontal, vertical and overhead concrete applications.

FINAL FINISH™ can also be used as a skim patch or trowel-down underlayment for horizontal repairs subjected to light traffic up to 1/4"

APPLICATION

Surface Preparation: The concrete must be sound and free of all foreign material, including oil, grease, dust, laitance or other surface contaminants. For best results, porous, or very dry/hot substrates should be pre-dampened with no standing water on the surface (SSD).

Mixing: Mix by hand or with a low speed drill. Add recommended amount of water into the container, followed by slowly adding the FINAL FINISH™ powder. Suggested water addition for FINAL FINISH™ is approximately 41% by weight or 16 pints (2.0 gals) per 40 lb pail. Mix 2-3 minutes until a uniform, smooth consistency is achieved. Covering the mixing container with a damp rag will extend the pot-life up to 3 hours @ 72F. Do not over-mix or retemper.

Placement: When placing with a trowel or sponge float, it may be necessary to use pressure to force FINAL FINISH™ into cracks, voids and honey-combed areas. FINAL FINISH™ retains its moisture and will spread easily. For applications in excess of 1/4" use Overcrete.

Placement - Walls: When applying FINAL FINISH™ to walls, first buildup low areas and fill voids with SpecPatch or Overcrete. Allow to harden. Apply a thin application of FINAL FINISH™ over entire surface area. Work in with a sponge float or trowel. If necessary, a second coat may be applied before the first coat has cured fully. Extreme weather conditions should be avoided, especially heat and wind.

Curing: FINAL FINISH™ will reach its final cure in twenty-four hours. Protect from rain or excess water until cured.

PACKAGING/COVERAGE

Available in 15 lb pails
 40 lb bags (60 bags per pallet)
 40 lb pails (36 pails per pallet)
Coverage of 40 lbs: approx 120 sq-ft @ 1/16"

CLEAN UP

Tools and equipment may be cleaned with water before FINAL FINISH™ hardens.

SHELF LIFE

Shelf life of unopened pails stored in a dry facility is 18 months. Excessive temperature differential and/or high humidity can shorten the shelf life expectancy. Store in a cool, dry area away from direct sunlight.

TYPICAL TEST DATA

Pot life @ 72°F	Up to 3 hours
Compressive Strength	
28 days	1500 psi
Water Requirements approx. 41% by Weight	
40 lbs of Final Finish™ will require:	15.8 to 16.0 pints water (1.9 to 2.0 gallons)
Color	Light Gray

LIMITATIONS/PRECAUTIONS

Do not retemper after initial mixing. Do not add other cements or additives to this product. Mixing equipment should be cleaned with water. Do not apply to wet surfaces.

Not intended as a wear surface but can be used as a trowel down underlayment under carpet, tile and other flooring surfaces.



1511 Baltimore Ave, Suite 600
 Kansas City, MO 64108
www.specchem.com 816.968.5600

LIMITATIONS/PRECAUTIONS

Do not allow repairs to freeze until the material has reached a minimum of 1000 psi compressive strength. In adverse temperatures, follow ACI recommendations for hot/cold weather concreting practices.

Minimum surface and ambient temperature of 45°F and rising is required at the time of application. For optimum results, condition material to between 65°F and 85°F.

Caution: Contains Portland Cement . Cement will cause irritation. Avoid contact. A dust respirator, safety goggles, and rubber gloves are recommended. Avoid prolonged contact with clothing. In case of contact with eyes, immediately flush with water for at least 15 minutes. Get prompt medical attention. Do not wear contact lenses when working with this product. DO NOT take internally. Keep out of reach of children.

Avoid hazards by following all precautions found in the Safety Data Sheet (SDS), product labels, and technical literature. Please read this information prior to using the product.

WARRANTY

NOTICE-READ CAREFULLY

CONDITIONS OF SALE

SpecChem offers this product for sale subject to and limited by the warranty which may only be varied by written agreement of a duly authorized corporate officer of SpecChem. No other representative of or for SpecChem is authorized to grant any warranty or to waive limitation of liability set forth below.

WARRANTY LIMITATION

SpecChem warrants this product to be free of manufacturing defects. If the product when purchased was defective and was within use period indicated on container or carton, when used, SpecChem will replace the defective product with new product without charge to the purchaser. SpecChem makes no other warranty, either expressed or implied, concerning this product. There is no warranty of merchantability. NO CLAIM OF ANY KIND SHALL BE GREATER THAN THE PURCHASE PRICE OF THE PRODUCT IN RESPECT OF WHICH DAMAGES ARE CLAIMED.

INHERENT RISK

Purchaser assumes all risk associated with the use or application of the product.



1511 Baltimore Ave, Suite 600
Kansas City, MO 64108

www.specchem.com 816.968.5600