

POR-ROK CONCRETE PATCH

Cement Based Vertical and Horizontal Repair Mortar

DESCRIPTION

Por-Rok Concrete Patch is a single component, cement based, fiber reinforced repair mortar designed for vertical and overhead applications. Por-Rok Concrete Patch can be built up to 4" on vertical applications.

Por-Rok Concrete Patch is designed to repair vertical and horizontal concrete and can be used on Bridge columns, parking structures, columns, spandrels beams, concrete ceilings, tunnels, pipes, pilings and any other vertical or overhead concrete repair application.

Por-Rok Concrete Patch is a light concrete grey color and can be sculpted after initial set.

FEATURES/BENEFITS

- Rapid setting
- Single component - Easy to use
- Shrinkage compensated
- Exceptional compressive and flexural strength
- Light grey in color to match existing concrete
- Excellent adhesion
- Strong Bond can be used to improve freeze thaw resistance and bond strength

APPLICATION

SUBSTRATE PREPARATION:

All surfaces must be sound, clean, free of loose or damaged concrete, dust, dirt and other contaminants that will interfere with bond.

Abrade the concrete to obtain a rough surface thereby promoting adhesion. The area should be saturated surface dry (SSD) with no standing water. The use of a vigorously scrubbed in no slump bond coat of Por-Rok Concrete Patch or a bonding agent like Strong Bond is recommended. This should be applied to all surfaces coming into contact with the patch. Do not allow bond coat to dry prior to the placement of Por-Rok Concrete Patch.

Steel Exposure and Rebar:

Completely expose and clean all reinforcing steel, ensuring a minimum clearance of 3/4" behind reinforcing steel. Perform reinforcing steel preparation in accordance with ICRI Technical Guidelines No. 03730. For best results patch area edges should be saw cut to a depth of 1/4".

MIXING:

Standard Mixing:

Mix close to repair area. Approximate initial set is 10-15 minutes at 70 degrees. Only mix what can be placed before initial set. Always mix by adding the dry product to the water. For each 50 lb. bag of Por-Rok Concrete Patch add 3.75 - 4.25 quarts of clean potable water (Roughly 1 part water to 5 parts powder). Use a low

APPLICATION CONT.

speed mortar mixer or a 1/2" drill with mixing paddle. Mix for a minimum of 90 seconds in order to obtain a uniform consistency. Do not re-temper.

Enhanced Mix:

Mix close to repair area. Approximate initial set is 10-15 minutes at 70 degrees. Only mix what can be placed before initial set. Always mix by adding the dry product to the liquid. Add 1 gallon of Strong Bond per 50 lb. bag of Por-Rok Concrete Patch (Roughly 1 part Strong Bond to 5 parts powder). Use a low speed mortar mixer or a 1/2" drill with mixing paddle. Mix for a minimum of 90 seconds in order to obtain a uniform consistency. Do not re-temper.

APPLICATION:

Immediately apply the fresh mortar to the surface, force Por-Rok Concrete Patch firmly into the properly prepared area insuring full contact with all bonding surfaces. Overfill the area and after initial set, using a steel trowel, sculpt Por-Rok Concrete Patch to the desired final profile, shaving from the center towards the bond edge at the existing surfaces. A water mist may help with final shaping.

In deep areas additional lifts can be made after the original patch has reached initial set (approximately 15 minutes). Score and roughen the original lift layer to improve bond between applications.

Por-Rok Concrete Patch used neat, can be placed in lifts up to 4" on vertical applications by holding the mortar in place until initial set takes place.

After initial set a damp sponge can be used to smooth to desired finish.

APPLICATION NOTES:

1. It is the responsibility of the contractor to review the complete technical datasheets of CGM products referenced above as more detailed information may be required. The information provided above acts only as a general guideline and may vary based on jobsite conditions.
2. Keep from freezing during and 24 hours after application
3. Do not add accelerators, admixtures or foreign chemicals



1511 Baltimore Ave, Suite 600
Kansas City, MO 64108

www.specchem.com 816.968.5600

APPLICATION CONT.

- On new concrete always test for Cure and Seals which inhibit bond. If Cure and Seals are present they must be removed by mechanical means prior to applying Por-Rok Concrete Patch.
- Cooler temperatures, inadequate ventilation and higher humidity can extend drying times.

CURING:

Cure in accordance with American Concrete Institute Procedure No. 308. Keep Por-Rok Concrete Patch moist and protected from high temperature, high wind, low humidity and direct sun causing rapid drying, by covering with wet burlap or plastic for up to 24 hours. A water based curing can be used.

TYPICAL TEST DATA

Compressive Strength (ASTM C109)	
1 day	3300 psi
7 days	4500 psi
28 days	6000 psi
Yield/Density	
Yield per bag	50 lb. Unit Yields: 0.46 ft. ³

PACKAGING

50 lb. bag : 58 per pallet
10 lb. pail : 160 per pallet
5 lb. pail : 320 per pallet

CLEAN UP

Clean tools with water immediately after use or by mechanical means once dry.

STORAGE

Store in cool dry place. Tightly seal package and do not expose to sun.

SHELF LIFE

12 months. Rotate your stock.

WARRANTY

NOTICE-READ CAREFULLY CONDITIONS OF SALE

SpecChem offers this product for sale subject to and limited by the warranty which may only be varied by written agreement of a duly authorized corporate officer of SpecChem. No other representative of or for SpecChem is authorized to grant any warranty or to waive limitation of liability set forth below.

WARRANTY LIMITATION

SpecChem warrants this product to be free of manufacturing defects. If the product when purchased was defective and was within use period indicated on container or carton, when used, SpecChem will replace the defective product with new product without charge to the purchaser. SpecChem makes no other warranty, either expressed or implied, concerning this product. There is no warranty of merchantability. NO CLAIM OF ANY KIND SHALL BE GREATER THAN THE PURCHASE PRICE OF THE PRODUCT IN RESPECT OF WHICH DAMAGES ARE CLAIMED.

INHERENT RISK

Purchaser assumes all risk associated with the use or application of the product.



1511 Baltimore Ave, Suite 600
Kansas City, MO 64108

www.specchem.com 816.968.5600