

# SPECLEVEL PCT-AGG

# SPEC<sup>CHEM</sup>

Solution to Service

## High Performance Self-Leveling Polishable Concrete Topping

A cement based, self-leveling polishable concrete topping designed for interior and exterior use. SpecLevel PCT-AGG produces a dense hard surface that can be diamond polished in as little as 24 hours. Mix SpecLevel PCT-AGG with water, pour or pump, and it will seek its own level to produce a smooth, hard wearable surface. SpecLevel PCT-AGG dries to a light concrete gray and will accept integral color or stains.



### ✓ Benefits

- SpecLevel PCT-AGG, when properly mixed, produces a self-leveling, wear topping with a flow time of 20 minutes at 70°F
- Self-leveling, requiring no troweling
- Can be easily pumped
- Produces a smooth, tough wearable surface
- Accepts integral color and concrete stains
- Can be diamond polished in 24 hours
- Creates a salt and pepper finish when polished
- Pre-extended with a special aggregate blend for an architectural polished concrete finish



## Usage

- Designed for polishing and decorative flooring applications
- Durable in dry and wet areas
- For finished floors in commercial, institutional and recreational facilities

## Packaging

- Available in 50 lb. bags. 1 bag covers approximately 15 sq/ft at 3/8"

TYPICAL TEST DATA			
<b>Set Time at 70 °F (ASTM C-266)</b>		<b>Bond Strength (ASTM C-882 modified)</b>	
<b>Initial Set</b>	<b>30 Minutes</b>	<b>7 Days</b>	<b>1450 PSI</b>
<b>Final Set</b>	<b>40 Minutes</b>	<b>Flexural Strength (ASTM C-348)</b>	
<b>Compressive Strength (ASTM C-109)</b>		<b>28 Days</b>	<b>1150 PSI</b>
<b>1 Day</b>	<b>3000 PSI</b>	<b>Yield/Density</b>	
<b>7 Days</b>	<b>4500 PSI</b>	<b>Yield Per Bag</b>	<b>.50 cu-ft (125 lbs/cu-ft)</b>
<b>28 Days</b>	<b>5500 PSI</b>		