

# High Performance Self-Leveling Polishable Concrete Topping

A cement based, self-leveling polishable concrete topping designed for interior and exterior use. SpecLevel PCT-AGG produces a dense hard surface that can be diamond polished in as little as 24 hours. Mix SpecLevel PCT-AGG with water, pour or pump, and it will seek its own level to produce a smooth, hard wearable surface. SpecLevel PCT-AGG dries to a light concrete gray and will accept integral color or stains.



## ✓ Benefits

- SpecLevel PCT-AGG, when properly mixed, produces a self-leveling, wear topping with a flow time of 20 minutes at 70°F
- Self-leveling, requiring no troweling
- Can be easily pumped
- Produces a smooth, tough wearable surface
- Accepts integral color and concrete stains
- Can be diamond polished in 24 hours
- Creates a terrazzo-like finish when polished
- Pre-extended with a special aggregate blend for an architectural polished concrete finish



## Usage

- Designed for polishing and decorative flooring applications
- Durable in dry and wet areas
- For finished floors in commercial, institutional and recreational facilities

## Packaging

- Available in 50 lb. bags. 1 bag covers approximately 15 sq/ft at 3/8"

TYPICAL TEST DATA			
Set Time at 70 °F (ASTM C-266)		Bond Strength (ASTM C-882 modified)	
Initial Set	30 Minutes	7 Days	1450 PSI
Final Set	40 Minutes	Flexural Strength (ASTM C-348)	
Compressive Strength (ASTM C-109)		28 Days	1150 PSI
1 Day	3000 PSI	Yield/Density	
7 Days	4500 PSI	Yield Per Bag	.50 cu-ft (125 lbs/cu-ft)
28 Days	5500 PSI		