

High Performance Self-Leveling Polishable Concrete Topping

A cement based, self-leveling polishable concrete topping designed for interior and exterior use. SpecLevel PCT produces a dense hard surface that can be diamond polished in as little as 24 hours. Mix SpecLevel PCT with water, pour or pump, and it will seek its own level to produce a smooth, hard wearable surface. SpecLevel PCT dries to a light concrete gray and will accept integral color or stains.



✓ Benefits

- SpecLevel PCT, when properly mixed, produces a self-leveling, wear topping with a flow time of 20 minutes at 70°F
- Self-leveling, requiring no troweling
- Can be easily pumped
- Produces a smooth, tough wearable surface
- Accepts integral color and concrete stains
- Can be diamond polished in 24 hours
- Creates a salt & pepper finish when polished
- Pre-extended with a special aggregate blend for an architectural polished concrete finish



Usage

- Designed for polishing and decorative flooring applications
- Durable in dry and wet areas
- For finished floors in commercial, institutional and recreational facilities

Packaging

- Available in 50 lb. bags. 1 bag covers approximately 15 sq/ft at 3/8"

| TYPICAL TEST DATA | | | |
|--|-------------------|--|----------------------------------|
| Set Time at 70 °F (ASTM C-266) | | Bond Strength (ASTM C-882 modified) | |
| Initial Set | 30 Minutes | 7 Days | 1450 PSI |
| Final Set | 40 Minutes | Flexural Strength (ASTM C-348) | |
| Compressive Strength (ASTM C-109) | | 28 Days | 1150 PSI |
| 1 Day | 3000 PSI | Yield/Density | |
| 7 Days | 4500 PSI | Yield Per Bag | .50 cu-ft (125 lbs/cu-ft) |
| 28 Days | 5500 PSI | | |