

SPECTILT WB

Premium reactive water-based tilt-up Cure/Bondbreaker

DESCRIPTION

SPECTILT WB is a chemically reactive water based tilt-up cure/bond breaker specially engineered to provide a clean, easy lift of tilt-up panels and meet the moisture retention of ASTM C309. **SPECTILT WB** contains no diesel, kerosene, waxes or silicones.

- Clean panels lift easier, no resin stains
- Chemically reactive
- VOC Compliant < 350g/l
- Resists foot traffic abrasion

APPLICATION

Curing New Concrete:

SpecTilt WB must be mixed or agitated before each use.

Do not dilute. When used as a cure, **SPECTILT WB** should be applied immediately after the final steel troweling, after the surface water has disappeared. Waiting too long to apply the cure coat can result in porous, dry casting slabs that will not yield favorable results. The entire slab must be completely covered. Applied on tightly steel troweled concrete @ 250-350 sq ft per gal.

Bond Breaker Coat:

Casting slab must be well cured, smooth and dense. Remove all dust, dirt, and other contaminants prior to application. **SPECTILT WB** should be applied just prior to placing reinforcing steel and within two weeks of pouring panels. Spray apply @ 400 sq ft per gal or to the point of rejection. Wait until dry and then apply a second coat at right angles to the previous coat. Coverage rate of second coat is typically 500-700 sq ft per gal. Complete uniform coverage is necessary on casting slab. If treated slab appears uneven or has light colored spots, this may indicate a porous slab that requires additional applications of bondbreaker. If after additional applications, these light spots persist, thoroughly wet affected areas with water to fill concrete pores. Squeegee off excess water and then immediately reapply **SPECTILT WB**. Allow bondbreaker to thoroughly dry. An adequate application is indicated only by the presence of a dry soap like feel apparent to the touch over the entire treated slab. Do not allow foot traffic until the slab is thoroughly dry.

Bond Breaker Coat on Old or Water Cured Concrete:

Verify that the concrete surface is free of curing compounds, salts or other substances that could adversely affect the performance of **SPECTILT WB**. The slab must be smooth, dense, well cured and clean. Prior to placing reinforcing steel and within two weeks of pouring panels, flood casting slab surface with clean water. Squeegee off excess water and immediately apply **SPECTILT WB** to the point of rejection. Wait until dry and then apply a second coat at right angles to the previous coat. Allow to thoroughly dry. As before, if light colored areas appear after drying, a porous slab may be indicated and reapplication will be necessary. The application rate can vary greatly depending upon the porosity of the slab and the ambient conditions. It is the contractors responsibility to ensure the even presence of **SPECTILT WB** at the surface of the casting slab prior to pouring concrete.

Before Pouring Concrete:

Ensure that the entire treated surface has a dry soap like feel to the touch. Test casting slab by sprinkling a few drops

APPLICATION (con't)

of water in several places. The water should bead up like on a newly waxed car. Fog the entire slab with water prior to pouring. When pouring concrete, avoid scouring the casting slab surface by using a deflection board. Heavy rains or rains prior to bond breaker coats drying may necessitate reapplication.

Stack Panels/Waste slabs:

Extra care must be used with stack panels and waste slabs as they tend to be more porous and can transfer water across their interface increasing the possibility of the "osmotic effect" thus leading to sticking. It is recommended that a SpecChem Cure & Seal or a double coat of cure/bond breaker be applied as the cure coat prior to the bond breaker coat to lessen the chance of sticking.

Painting of Panels:

If **SPECTILT WB** has been properly applied and has not been over applied, painting of the panels can be performed as soon as the moisture content in the concrete is at an acceptable level for the paint manufacturer. Coating manufacturer's instructions for proper surface preparation must be followed and supersedes information in this data sheet.

Other Instructions:

Do not apply in rain or if rain is forecast within 12 hours of application. Panels exposed to rain may require reapplication @ 500-700 sq-ft per gal. Not recommended for use as a bond breaker on broom or rough finished concrete. Spray apply for best results with a low pressure sprayer (Chapin, Hudson, etc) with a 1/2 gal/min tip in a fine uniform spray pattern. Always ensure the complete presence of bond breaker prior to pouring panels.

Please contact SpecChem technical service for special instructions on Casting Slabs or Stack Panels and when using concrete mixes containing pozzolans (slag, fly ash).

Hot weather can cause premature drying of the concrete casting slab surface, causing it to be overly-porous, exhibit cracking and crazing and have reduced surface strength. The use of an evaporation retardant such as **SpecFilm**, can greatly reducing the possibility of plastic shrinkage cracking, crazing, and uneven/wavy surfaces.

Hot Weather Tips for Tilt-Up

One of the best ways to offset the effects of hot weather is with modified curing and bond breaker application techniques.

SpecChem makes the following recommendations when using **SpecTilt WB** Cure and Bond Breaker:

1) Apply the **SpecTilt WB** cure coat **immediately** after final finishing and preferably prior to control joint cutting. Apply to the point of uniform surface film accumulation. Slabs with exceptionally porous surfaces or rougher finishes may re-

SPECCHEM 
Solution to Service

1511 Baltimore Ave, Suite 600
Kansas City, MO 64108

www.specchemllc.com

866.791.8700

Hot Weather Application

quire heavier applications to ensure adequate holdout and uniform surface accumulation. The cure application is the most critical to assure an adequate base for the subsequent bond breaker coats. In hot weather, the proper timing and application rate are essential and the cure coat should be applied at a minimum 250-300 sq-ft per gal.

2) Immediately before application of the **SpecTilt WB** bond breaker coats, saturate the casting slab surface with water, thoroughly removing the excess water with a squeegee or compressed air. This practice is especially recommended if the slab was improperly cured, the application of the cure coat was delayed or if the slab is suspected of being porous. This step cools the casting slab and allows the water to "take up" any remaining porosity just before the bond breaker coats are applied.

3) Apply successive **SpecTilt WB** bond breaker coats until the casting slab surface appears uniformly dark for a minimum of 2-4 hours and has a dry, soapy feel in all areas. Do not allow **SpecTilt WB** to accumulate in low spots or depressions.

Panel Concrete Placement

Very porous casting slabs can cause the "osmotic effect" to occur, even when adequate bond breaker has been applied. In simple terms, the "osmotic effect" refers to the natural tendency of water to migrate from wet to dry. This means that when fresh panel concrete is placed on a hot porous casting slab, water will migrate from the fresh concrete into the dry casting slab, leaving the wall panel surface concrete without adequate water for proper hydration. This can result in dusting or skin pull off on the panel surfaces. To minimize the osmotic effect, immediately prior to placement of the panel concrete, saturate the casting slab with water, and then thoroughly squeegee off or blow off the excess water with compressed air. No surface water should be present on the casting bed surface prior to panel concrete placement.

CLEANING

Tools, sprayers and other equipment may be cleaned with water prior to the bond breaker drying. SpecChem Orange Peel or other approved solvents may be used to clean off the dried bond breaker. With proper application, the casting slab and panels may not require cleaning but may be washed with a mild alkaline detergent to remove any over application.

PACKAGING

SPECTILT WB is packaged in 55 gal drums and 5 gal pails.

SHELF LIFE

Do not allow to freeze! Store material in the original tightly closed containers. Do not allow the accumulation of water, dirt or other contaminants. Store SPECTILT WB between 45-85 degrees F. Prolonged exposure to high temperatures (above 90 degrees) can significantly reduce shelf-life. Properly stored, shelf-life is 1 year from the date of manufacturer.

LIMITATIONS

DO NOT ALLOW TO FREEZE. Avoid over applications. SPECTILT WB must be completely dry prior to pouring concrete. Do not walk on bond breaker until completely dry. For best performance, flood the pour area with water immediately before pouring concrete. Do not apply below freezing (32 F).

Important: If the concrete is cured without using a SpecChem cure/bond breaker or without a SpecChem ASTM C 309 curing compound, please contact a SpecChem representative for technical support.

DO NOT EXPOSE TO OR APPLY NEAR FIRE OR FLAMES. FOR WELL VENTILATED OR EXTERIOR USE ONLY!

Mix Design: The use of pozzolans such as flyash and slag in the casting bed typically slow the rate of hydration, and reduce bleed making the casting bed more susceptible to drying shrinkage and increase surface porosity at the time of cure application. This increased porosity will require a heavier cure coat to achieve adequate hold-out. Contact SpecChem for further information.

SpecChem strongly recommends that no pozzolans be used in the panel concrete.

PRECAUTIONS

**DO NOT CUT OR WELD CONTAINER
KEEP AWAY FROM OPEN FLAME
INDUSTRIAL USE ONLY**

Additional precautions, safety information and first aid are contained in the Safety Data Sheet.

WARRANTY

NOTICE-READ CAREFULLY CONDITIONS OF SALE

SpecChem offers this product for sale subject to and limited by the warranty which may only be varied by written agreement of a duly authorized corporate officer of SpecChem. No other representative of or for SpecChem is authorized to grant any warranty or to waive limitation of liability set forth below.

WARRANTY LIMITATION

SpecChem warrants this product to be free of manufacturing defects. If the product when purchased was defective and was within use period indicated on container or carton, when used, SpecChem will replace the defective product with new product without charge to the purchaser. SpecChem makes no other warranty, either expressed or implied, concerning this product. There is no warranty of merchantability. NO CLAIM OF ANY KIND SHALL BE GREATER THAN THE PURCHASE PRICE OF THE PRODUCT IN RESPECT OF WHICH DAMAGES ARE CLAIMED.

INHERIT RISK

Purchaser assumes all risk associated with the use or application of the product.

SPECCHEM 
Solution to Service

1511 Baltimore Ave, Suite 600
Kansas City, MO 64108

www.specchemllc.com 866.791.8700