


TECHNICAL DATA

PAVECURE WW CALTRANS

High solids, white pigmented, wax based concrete curing compound  GREENCONSCIOUS

DESCRIPTION

PAVECURE WW CALTRANS is a high solids wax and water based white pigmented concrete curing compound. When properly applied, PAVECURE WW CALTRANS forms a continuous membrane that controls curing for strong and durable concrete. The white pigment reflects the sun's rays to help keep the concrete surface cooler and to prevent excessive heat build-up. PAVECURE WW CALTRANS is ideal for application on exterior, horizontal surfaces such as highway and bridge paving applications when proper curing is required.

FEATURES/BENEFITS

- Reduces shrinkage; retains moisture to reduce "plastic shrinkage cracks"
- Improves durability; proper curing will increase the long life of concrete.
- Enhances performance; increases compressive strength and wear resistance
- **Actual/Maximum V.O.C. Content = 20 g/l**
- High reflectivity

SPECIFICATIONS/COMPLIANCE

Meets ASTM C-309, Type II, Class A
AASHTO M-148, Type II, Class A
Formulations available for specific States & CRD C 300 specifications.
Meets Caltrans Standard Specification 90-1.02J for Curing compound no. 3
SCAQMD Rule 1113; FOR ROADWAYS AND BRIDGES ONLY (Not for use on curbs, gutters, sidewalks, islands, driveways and other misc. concrete areas)
DO NOT THIN

APPLICATION

Coverage: Ready to use. Do not dilute. Apply with a manual sprayer, power sprayer or paving train. Avoid puddles. Apply in accordance with recommended coverage rates.

Curing: 200 sq ft / gal

New Concrete: PAVECURE WW CALTRANS should be applied as soon as the surface water has disappeared and the concrete surface will not be marred by the walking applicator. At this point, apply in a uniform coat.

CLEAN UP

Tools and equipment should be flushed and cleaned with water immediately after use. Use SpecChem Solvent 100 or a cleaning solvent for sprayers to remove cured or residual material

PACKAGING

275 gallon totes
55 gallon drums
5 gallon pails.

STORAGE/SHELF LIFE

Shelf life of PAVECURE WW CALTRANS in the original tightly closed containers is one year from the date of manufacture. Do not allow the accumulation of water, dirt, or other contaminants. Avoid prolonged exposure to heat in excess of 100°F.

TYPICAL TEST DATA

Moisture Loss— California Test Method 534

Applied at 200 ft ² /gal	<0.15kg/m ² @24 hrs.
Test Requirement	0.15kg/m ² max. @ 24 hrs.

Reflectivity

Greater than 60%

LIMITATIONS/PRECAUTIONS

Do not allow to freeze. If freezing takes place, consult SpecChem. Do not mix or contaminate with solvent, diesel fuel or other thinning agents.

Do not over agitate with compressed air or recirculating pump. Keep out of reach of children. Do not take internally. Do not breathe vapors. Avoid prolonged contact with skin. If swallowed, do not induce vomiting - call physician. Wear rubber gloves, goggles, and protective clothing.

Do not use on concrete that is to accept a secondary topping without first consulting the manufacturer.

Avoid hazards by following all precautions found in the Material Safety Data Sheet (MSDS), product labels and technical literature. Please read all information prior to using the product.

Clean and thoroughly flush all equipment with warm water.

DO NOT EXPOSE TO OR APPLY NEAR FIRE OR FLAMES. FOR WELL VENTILATED OR EXTERIOR USE ONLY!

WARRANTY

NOTICE-READ CAREFULLY CONDITIONS OF SALE

SpecChem offers this product for sale subject to and limited by the warranty which may only be varied by written agreement of a duly authorized corporate officer of SpecChem. No other representative of or for SpecChem is authorized to grant any warranty or to waive limitation of liability set forth below.

WARRANTY LIMITATION

SpecChem warrants this product to be free of manufacturing defects. If the product when purchased was defective and was within use period indicated on container or carton, when used, SpecChem will replace the defective product with new product without charge to the purchaser. SpecChem makes no other warranty, either expressed or implied, concerning this product. There is no warranty of merchantability. NO CLAIM OF ANY KIND SHALL BE GREATER THAN THE PURCHASE PRICE OF THE PRODUCT IN RESPECT OF WHICH DAMAGES ARE CLAIMED.

INHERENT RISK

Purchaser assumes all risk associated with the use or application of the product.

SPECCHEM 
Solution to Service

1511 Baltimore Ave, Suite 600
Kansas City, MO 64108
www.specchem.com 866.791.8700